

TECHNICAL DATA SHEET

January 2025, Issue 1



LAMBDA CORE is a closed-cell thermosetting polyisocyanurate (polyiso) foam core, integrally bonded to inorganic coated glass tissue facers on both sides. These boards have a Zero Ozone Depletion Potential (ODP) and <1 Global Warming Potential (GWP).

Available in 25 mm to 100 mm thickness, 1 220 mm wide; offered in various lengths.

APPLICATION:

Laminating on a continuous or discontinuous line for thermal insulation panels, where optimal thermal and fire performance is required in the built environment.

PHYSICAL PROPERTIES

THERMAL CONDUCTIVITY	λ Lambda value 0.024 W/m.K @22° C mean, aged-tested in accordance with ASTM C518
DENSITY	Overall density 40 Kg/m ³
WATER ABSORPTION	Zero (Below ambient temperature ranges a vapour barrier is recommended)
TEMPERATURE RANGE	-60° C to 120° C with no physical property degradation
THICKNESS	25 mm to 100 mm
WIDTH	1 220 mm
THICKNESS TOLERANCE	± 2 mm
COMMON BUILDING CHEMICAL RESISTANCE	Alkaline, Solvents and Paints
TOXICITY	NES 713 (Report available on request)
ADHESIVE RECOMMENDED	Polyurethane-based systems preferred

HANDLING AND STORAGE

LAMBDA CORE insulation boards are delivered wrapped in branded plastic packaging and to be stored on a flat surface away from the elements.

Learn more at: www.lambdaboard.co.za

PROUD MEMBERS OF:



DISAVOWAL: The information set forth herein is furnished free of charge and is based on technical data that RIGIFOAM believes to be reliable. It is intended for use by persons having technical skill and at their own discretion and risk. Since some conditions of use are outside our control, we make no warranties, express or implied, and assume no liabilities in connection with any use of this information. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patent.